



TRICOR REFINING, LLC

Producers of GOLDEN BEAR PRESERVATION PRODUCTS

1134 Manor St. • Oildale, CA 93308 / P.O. Box 5877 • Bakersfield, CA 93388
Phone 661.393.7110 – Fax 661.393.2083

SPECIFICATIONS FOR MC-800

Test Description	Requirements	
Kinematic Viscosity at 60°F (140°F) centistokes	800 min.	1600 max.
Flash Point (Tab. open-cup) degrees C° (F)	66 min (150)	n/a
Water percent	n/a	0.2 max
Distillation test:		
Distillate percentage by volume of total		
Distillate to 360°C (680°F)	n/a	n/a
to 225° C (437° F)	0 min.	35 max
to 260° C (500° F)	45 min.	80 max
to 315° C (600° F)		
Residue from distillation to 360°C (680° F)		
Volume percentage of sample by difference	75 min.	n/a
Tests on residue from distillation:		
Absolute viscosity at 60° C (140° F) poises	300 min.	1200 max
Ductility, 5cm/cm, cm.	100 min.	n/a
Solubility in Trichloroethylene, %	99.0 min.	n/a